

10/076,892
Page 3

AMENDMENTS TO THE CLAIMS

1. - 4. (Cancelled)
5. (Presently amended) An extended release tablet comprising a plurality of granules consisting of potassium chloride crystals between about 20 to about 60 mesh, and a continuous coating on the crystals, the coating consisting of a thermoplastic cellulose ether.
6. (Original) The tablet of claim 5, wherein the granules are essentially free of surfactants or processing aids and agents.
7. (Original) The tablet of claim 5, wherein the potassium chloride crystals comprise approximately 75.3% by weight based on the total weight of the tablet.
8. (Original) The tablet of claim 5, wherein the thermoplastic cellulose ether is ethylcellulose.
- b1 9. (Original) The tablet of claim 8, wherein ethylcellulose comprises approximately 15.5% by weight based on the total weight of the tablet.
10. (Original) The tablet of claim 5, wherein the tablet contains about 10 mEq to about 20 mEq potassium provided by the potassium chloride crystals.
11. (Original) The tablet of claim 5, wherein the tablet contains 10 mEq potassium, 15 mEq potassium, or 20 mEq potassium provided by the potassium chloride crystals.
12. (Presently amended) A pharmaceutical dosage unit in tablet form comprising a plurality of granules having an internal core of potassium chloride between about 20 to about 60 mesh and ~~an~~ a continuous external coating consisting of ethylcellulose, wherein the granules are essentially free of surfactants or processing aids and agents.

10/076,892
Page 4

13. (Original) The tablet of claim 12, wherein the core of potassium chloride comprises approximately 75.3% by weight based on the total weight of said tablet.
14. (Original) The tablet of claim 12, wherein the ethylcellulose comprises approximately 15.5% by weight based on the total weight of said tablet.
15. (Original) The tablet of claim 12, wherein the tablet contains about 10 mEq to about 20 mEq potassium provided by the potassium chloride.
16. (Original) The tablet of claim 12, wherein the tablet contains 10 mEq potassium, 15 mEq potassium, or 20 mEq potassium provided by the potassium chloride.
17. (Original) A process to produce ethylcellulose-coated potassium chloride granules comprising the steps of:
- i) forming a fluidized bed of potassium chloride crystals at a dew point of about 10-20° C,
 - ii) spraying the fluidized crystals with a mixture consisting of ethylcellulose, alcohol and water sufficient to coat the crystals, and
 - iii) drying the coated crystals to remove the water and alcohol to provide coated potassium chloride granules.
18. (Original) The process according to claim 17 wherein the dew point in step i) is 15° C.
19. (Original) The process according to claim 17 wherein the coated potassium chloride granules of step iii) are essentially free of surfactants or processing aids and agents.
20. (Original) The process according to claim 17 wherein the alcohol is methyl alcohol.
21. (Original) The process according to claim 20 wherein the mixture of step ii) is about 10.3% ethylcellulose, 2.1% water and 87.6% methyl alcohol, by weight.

10/076,892
Page 5

22. (Original) A method of manufacturing ethylcellulose-coated potassium chloride granules comprising the steps of:
- i) forming a fluidized bed of potassium chloride crystals,
 - ii) spraying the fluidized crystals with a mixture consisting of ethylcellulose, alcohol, and sufficient water to control the buildup of static charge so as to enable substantially complete coating of the crystals, and
 - iii) drying the coated crystals to remove the water and alcohol to provide coated potassium chloride granules.
23. (Original) The method of claim 22 wherein the coated potassium chloride granules of step iii) are essentially free of surfactants or processing aids and agents.
24. (Original) The method of claim 22 wherein the mixture of step ii) comprises 0.5 – 2% water, by weight.
- b1 25. (Original) The method of claim 22 wherein the alcohol is methyl alcohol.
26. (Original) The method of claim 25 wherein the mixture of step ii) is about 10.3% ethylcellulose, 2.1% water and 87.6% methyl alcohol, by weight.
27. (Original) A method for customizing a patient's supplemental potassium dosage regimen, the method comprising:
- i) providing pharmaceutical dosage units containing about 10 mEq potassium, 15 mEq potassium, and 20 mEq potassium; and
 - ii) administering the 10 mEq, 15 mEq, and 20 mEq dosage units in suitable combination to meet a patient's supplemental potassium requirements.
28. (Presently amended) A pharmaceutical dosage unit in tablet form comprising a plurality of granules having an internal core of potassium chloride between about 20 to about

10/076,892
Page 6

60 mesh and ~~an~~ a continuous external extended release coating, wherein the dosage unit contains 15 mEq potassium.

29. (Previously presented) The dosage unit of claim 28, wherein the extended release coating comprises ethylcellulose.

30. (Previously presented) The dosage unit of claim 28, wherein the granules are essentially free of surfactants or processing aids and agents.

31. (New) A process to produce a pharmaceutical dosage unit in tablet form, the dosage unit comprising ethylcellulose-coated potassium chloride granules, the method comprising the steps of:

- B1
cont
- i) forming a fluidized bed of potassium chloride crystals;
 - ii) spraying the fluidized crystals with a mixture consisting of ethylcellulose, alcohol and water sufficient to coat the crystals;
 - iii) drying the coated crystals to remove the water and alcohol to provide coated potassium chloride granules; and
 - iv) compressing a plurality of coated potassium chloride granules into a tablet to yield the pharmaceutical dosage unit.

32. (New) The process according to claim 31, wherein the tablet further comprises a compression aid and a disintegrant.

33. (New) The process according to claim 32, wherein the compression aid comprises microcrystalline cellulose, and the disintegrant comprises croscarmellose sodium.

34. (New) The process according to claim 31, wherein the tablet comprises, by weight:
about 75.3% potassium chloride;
about 15.5% ethylcellulose;
about 8.7% microcrystalline cellulose; and
about 0.5% croscarmellose sodium.